

PRODUCT INFORMATION

Solder liquid „KD“

<u>Description of product</u> :	Solder liquid “KD”
<u>Description of standard</u> :	DIN EN 29454.1, type 3.1.1.A (DIN 8511, F-SW 21)
<u>Condition</u>	liquid
<u>Chemical composition</u> :	Flux on a basis of zinc chloride and ammonium chloride in organic composition.
<u>Form of delivery</u> :	100 g bottles with brush inset 250 g bottles with brush inset 500 g bottles with brush inset 1.000 g bottles with brush inset Other bottles sizes are deliverable on request.
<u>Application</u> :	Flux for the soft soldering of copper and copper alloys.
<u>Removal of the residues after soldering</u> :	The flux residues are corrosive and have to be thoroughly removed with warm water (perhaps neutralization, ultrasound).
<u>Advices</u> :	For further fluxes of same and other ISO-numbers in liquid, powder or paste form please refer to our delivery programme. Please do not hesitate to contact us for further information.

9/2004

All information about our products are the result of our long standing experience, which we would like to pass on to our customers. Since we do not have any influence on the application with our products, please see the warranty claims in our conditions of sale because our liability is limited.